

LUMID GP1000B(W)

Injection Molding, PA66

Description

General Purpose, Low Viscosity

Application

Buckles, Chair Nob

Properties	Test Condition	Test Method	Unit	Typical Value
Physical				
Specific Gravity		ASTM D792	-	1.14
Molding Shrinkage, 3.2mm		ASTM D955	%	1.3 ~ 2.0
Melt Flow Rate		ASTM D1238	g/10min	
Water Absorption	23°C, 24hrs	ASTM D570	%	1.7
Mechanical				
Tensile Strength, 3.2mm		ASTM D638		
@ Yield	50mm/min		kg/cm ²	820
Tensile Elongation, 3.2mm		ASTM D638		
@ Break	50mm/min		%	50
Flexural Strength, 6.4mm	2.8mm/min	ASTM D790	kg/cm ²	1,150
Flexural Modulus, 6.4mm	2.8mm/min	ASTM D790	kg/cm ²	28,000
IZOD Impact Strength, 6.4mm (Notched)	23°C -30°C	ASTM D256	kg·cm/cm kg·cm/cm	5
IZOD Impact Strength, 3.2mm (Notched)	23°C -30°C	ASTM D256	kg·cm/cm kg·cm/cm	
Rockwell Hardness	R-Scale	ASTM D785	-	120
Thermal				
Melting Temperature		ASTM D3418	°C	260
Heat Deflection Temperature, 6.4mm (Unannealed)	18.6kg 4.6kg	ASTM D648	°C °C	75 230
Coefficient of Linear Thermal Expansion		ASTM D696		
Flow			10 ⁻⁵ m/m°C	8
Cross-flow			10 ⁻⁵ m/m°C	
Flammability 0.7mm		UL94	class	V-2

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection moulded specimens and after 48 hours storage at 23°C, 50% relative humidity.

Updated : 1-Jun-14

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

LUMID GP1000B(W)

Injection Molding, PA66

Description

General Purpose, Low Viscosity

Application

Buckles, Chair Nob

Electrical

Property	Test Condition	Standard	Unit	Value
Surface Resistivity		IEC 60093	Ohm	
Volume Resistivity	23 °C	ASTM D257	Ohm·cm	1.0E+14
Arc Resistance	23 °C	ASTM D495	sec	190
Dielectric Strength, 1mm	23 °C	ASTM D149	kV/mm	23
Dielectric Constant (10 ⁶ Hz)	23 °C	ASTM D150		3

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection molded specimens and after 48 hours storage at 23 °C, 50% relative humidity.

Processing Guide (Injection Molding)

Processing Parameters	Unit	Value	
Drying Temperature	°C	80 ~ 100	
Drying Time	hrs	4 ~ 5	
Maximum Moisture Content	%	0.1	
Melt Temperature	°C	260 ~ 280	
Cylinder Temperature	Rear	°C	255 ~ 270
	Middle	°C	260 ~ 275
	Front	°C	260 ~ 275
Nozzle Temperature	°C	260 ~ 280	
Mold Temperature	°C	60 ~ 90	
Back Pressure	Hydraulic Type	kg/cm ²	5~20
	Electric Type		50~200
Screw Speed	rpm	60~200	

Note) Back Pressure & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

Updated : 1-Jun-14

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.